

номер материала	DIN EN - D	AFNOR - F	BS - UK	JIS
0.6010	GG10	—	Grade 100	FC 100
0.6015	GG15	FGL 150	Grade 150	FC 150
0.6020	GG20	FGL 200	Grade 220	FC 200
0.6025	GG25	FGL 250	Grade 250, 260	FC 250
0.6030	GG30	FGL 300	Grade 300	FC 300
0.6035	GG35	FGL 350	Grade 350	FC 350
0.6655		L-NUC 15 6 2	F1	
0.6656		L-NUC 15 6 3	F1	
0.6660		L-NC 20 2	F2	
0.6661		L-NC 20 3	F2	
0.6676		L-NC 30 3	F3	
0.7040	GGG40	FGS 400-15	Grade 420/12	FCD 400
0.7043	GGG40.3	FGS 370-17	Grade 370/12	FCD 370
0.7050	GGG50	FGS 500-7	Grade 500/7	FCD 500
0.7060	GGG60	FGS 600-3	Grade 600/3	FCD 600
0.7070	GGG70	FGS 700-2	Grade 700/2	FCD 700
0.7080	GGG80	FGS 800-2	Grade 800/2	FCD 800
0.7652		S-NM 13 7	S 6	
0.7660		S-NC 20 2	S 2	
0.7661		S-NC 20 3	S 2	
0.7670		S-N 22	S 2 C	
0.7673		S-NM 23 4	S 2 M	
0.7676		S-NC 30 3	S 3	
0.7677		S-NC 30 1	S 3	
0.8035	GTW35	MB 35-7	W 35-04	FCMW 330
0.8038		MB 380-12	—	
0.8040	GTW40	MB 400-5	W 40-05	FCMW 370
0.8045	GTW45	MB 450-7	W 45-07	FCMWP 440
0.8135	GTS35	MN 350-10	B 35-12	FCMB 340
0.8145	GTS45	MP 50-5	P 45-06	
0.8155	GTS55	MP 60-3	P 55-04	
0.8165	GTS65	—	P 65-02	FCMP 540
0.8170	GTS70	MP 70-2	P 70-02	FCMP 690
0.9620	G-X 260 NiCr 4-2		Grade 2 A	
0.9625	G-X 330 NiCr 4-2		Grade 2 B	
0.9630	G-X 300 CrNiSi 9-5-2		Grade 2 C, D, E	
0.9635	G-X 300 CrMo 15-3		Grade 3 A, B	
0.9640	G-X 300 CrMoNi 15-2-1		Grade 3 A, B	
0.9645	G-X 260 CrMoNi 20-2-1		Grade 3 C	
0.9650	G-X 260 Cr 27		Grade 3 D	
0.9655	G-X 300 CrMo 27-1		Grade 3 E	
0.xxx	GGV - 30			FCV 300
0.xxx	GGV - 40			FCV 400
1.0301	C 10	XC 10	045 M 10040 A 10	S 10 C
1.0401	C 15	XC 12, XC 18	080 M 15	S 15 C
1.0402	C 22	1 C 22, XC 18, XC 25	1 C 22, 070 M 20	S 20 C, S 2 C
1.0406	C 25	1 C 25	070 M 26	S 25 C
1.0501	C 35	XC 38, 1 C 35	080 M 36, 1 C 35	S 35 C
1.0503	C 45	1 C 45, XC 48 H 1	1 C 45, 080 M 46	S 45 C
1.0511	C 40	1 C 40, XC 42 H 1	080 M 40, 1 C 40	S 40 C
1.0528	C 30	C 30	1 C 30, XC 32	S 30 C
1.0535	C 55	1 C 55, XC 55 H 1	1 C 55, 070 M 55	S 55 C
1.0540	C 50	1 C 50	1 C 50, 080 M50	S 50 C
1.0570	S355J2G3	E 36-3, E 36-4	Fe 510 D1 FF, 50/35	SM 490 __, SM 520 B
1.0601	C 60	1 C 60, AF 70 C 55	1 C 60, 080 A 67	S 58 C
1.0715	9 SMn 28	S 250	080 M 15, 230 M 07	SUM 22
1.0718	9 SMnPb 28	S 250 Pb	—	SUM 22 L, SUM 23 L
1.0721	10 S 20	13 MF 4, 10 F 1	210 M 15	
1.0722	10 SPb 20	CC 10 Pb, 10 PbF 2	—	SUM 12
1.0726	35 S 20	35 MF 6	212 M 36	SUM 41
1.0727	45 S 20	45 MF 61, 45 MF 4	212 M 36	SUM 42
1.0728	60 S 20	—	—	
1.0736	9 SMn 36	S 300	240 M 07	SUM 25
1.0737	9 SMnPb 36	S 300 Pb	—	SUM 24 L
1.1121	Ck 10 (C 10 E)	XC 10	045 M 10, 040 A 10	S 9 Ck, S 10 C
1.1141	Ck 15 (C 15 E)	XC 12, XC 15	080 M 15, 040 A 15	S 15, S 15 Ck
1.1151	C 22 E	2 C 22, XC 18/25	055 M 15	S 20 C, S 20 Ck, S 22 C
1.1157	40 Mn 4	35 M 5, 40 M 5	150 M 36	
1.1158	C 25 E	2 C 25, XC 25	070 M 26	S 25 C, S 28 C
1.1170	28 Mn 6	28 Mn 6, 35 M 5	28 Mn 6, 150 M 19	SMn 433