

UNI - I	UNE - E	AISI - US	состояние	группа материала
		630	AU-PH	14.4
X 8 CrNiNb 18 11		347	AU	14.1
		—	AU	14.1
		302 HQ	AU	14.1
X 2 CrNiMo 17.12		17-07 PH	AU-PH	14.4
X 6 CrNiMoTi 17 12		316 Ti	AU	14.1
X 6 CrNiMoTi 17 12		(316 Ti)	AU	14.1
X 6 CrNiMoNb 17 12		316 Cb	AU	14.1
GX 6 CrNiMoNb 20 11	—	—	AU	14.1
X 6 CrNiMoNb 17 13		316 Cb, (318)	AU	14.1
—	—	—	FE	10–11
X 45 CS 8	—	HNV 3		31–32
—	—	409		31–32
X 10 CrAl 12	X 10 CrAl 13	405	FE	12
—	—	—		12
X 8 Cr 17	X 10 CrAl 18	430		12
—	—	—		31–32
X 16 Cr 26		446		12
—	X 15 CrNiSi 25 04	—	DU	14.2
—	X 10 CrNiSi 20	309	AU	14.1
X 6 CrNi 23 14	—	309 S	AU	14.1
X 16 CrNiSi 25 20	X 15 CrNiSi 25 20	310	AU	14.1
—	—	310 S	AU	14.1
—	X 12 NiCrSi 36 16	330		31–32
—	—	EV 8		10
X 45 CrNiW 18 9	—	EV 9		31–32
—	—	EV 11		31–32
—	X 10 NiCrAlTi 32 20	—	S-AU	31–32
X 6 CrNiTi 18 11	—	321, 321 H		31–32
—	—	304H	AU	14.1
—	—	—	var ¹	6–9
60 SiCr 8	F.1442	9260	var ¹	6–9
—	F.1581	4320	var ¹	6–9
16 NiCrMo 12	F.1525	—	var ¹	6–9
36 CrNiMo 4, 39 NiCrMo 3 1	36 CrNiMo 4, 40 NiCrMo 4	—	var ¹	6–9
SNCM 630	30 CrNiMo 8, 32 NiCrMo 16	—	var ¹	6–9
34 CrNiMo 6	34 CrNiMo 6	4340	var ¹	6–9
18 NiCrMo 12	F.1560	—	var ¹	6–9
38 Cr 2	38 Cr 2, 38 Cr 3	—	var ¹	6–9
46 Cr 2	46 Cr 2	—	var ¹	6–9
—	—	—	var ¹	6–9
34 Cr 4	34 Cr 4	5132	var ¹	6–9
37 Cr 4	37 Cr 4, 38 Cr 4	5135	var ¹	6–9
41 Cr 4	41 Cr 4, 42 Cr 4	5140	var ¹	6–9
34 CrS 4	34 CrS 4	—	var ¹	6–9
37 CrS 4	37 Cr 4, 38 Cr 4-1	—	var ¹	6–9
41 CrS 4	41 CrS 4, 42 Cr 4-1	—	var ¹	6–9
48 Si 7	F.1450	9260	var ¹	6–9
16 MnCr 5	F.1516	—	var ¹	6–9
20 MnCr 5	F.1523	—	var ¹	6–9
55 Cr 3	—	5155	var ¹	6–9
25 CrMoS 4, 25 CrMo 4	25 CrMoS 4, 30 CrMo 4-1	—	var ¹	6–9
25 CrMo 4	25 CrMo 4, 30 CrMo 4	4130	var ¹	6–9
34 CrMo 4, 35 CrMo 4	34 CrMo 4, 35 CrMo 4	4137	var ¹	6–9
42 CrMo 4	42 CrMo 4	—	var ¹	6–9
34 CrMoS 4, 35 CrMo 4	34 CrMoS 4, 35 CrMo 4	—	var ¹	6–9
42 CrMoS 4, 42 CrMo 4	42 CrMoS 4, 40 CrMo 4-1	—	var ¹	6–9
50 CrMo 4	50 CrMo 4	4150	var ¹	6–9
16 NiCrMo 2	F.1523	8620	var ¹	6–9
20 NiCrMo 2	—	8625	var ¹	6–9
—	—	—	var ¹	6–9
51 CrMoV 4	—	—	var ¹	6–9
51 CrV 4, 50 CrV 4	51 CrV 4	6150	var ¹	6–9
—	35 CrAlMo 5	A 355/D	var ¹	6–9
41 CrAlMo 7	41 CrAlMo 7	A 355/A	var ¹	6–9
31 CrMo 12	31 CrMo 12	—	var ¹	6–9
36 CrMoV 12	—	—	var ¹	6–9
—	—	A 355/C	var ¹	6–9