

Hole Finishing

HSR™ Application Data • Series 050271



■ Series 050271 • Solid Carbide • Helical Flute • Grade K10F™ • Metric

Material Group										
		Cutting Speed — vc Range — m/min			Recommended Feed Rate per Rev					
		min		max	Tool Diameter	3,16–4,80	4,81–7,15	7,16–9,59	9,60–12,70	12,70–15,00
P	1	50	–	70	mm/r	0,20–0,40	0,30–0,50	0,35–0,65	0,40–0,80	0,50–0,90
	2	40	–	60	mm/r	0,20–0,40	0,30–0,50	0,35–0,65	0,40–0,80	0,50–0,90
	3	40	–	60	mm/r	0,20–0,40	0,30–0,50	0,35–0,65	0,40–0,80	0,50–0,90
	4	30	–	40	mm/r	0,20–0,40	0,30–0,50	0,35–0,65	0,40–0,80	0,50–0,90
	5	20	–	30	mm/r	0,20–0,40	0,30–0,50	0,35–0,65	0,40–0,80	0,50–0,90
	6	10	–	20	mm/r	0,20–0,30	0,20–0,40	0,30–0,50	0,30–0,60	0,35–0,65
M	1	10	–	20	mm/r	0,20–0,30	0,20–0,40	0,30–0,50	0,30–0,60	0,35–0,65
	2	10	–	20	mm/r	0,20–0,30	0,20–0,40	0,30–0,50	0,30–0,60	0,35–0,65
	3	10	–	20	mm/r	0,20–0,30	0,20–0,40	0,30–0,50	0,30–0,60	0,35–0,65
K	1	30	–	50	mm/r	0,35–0,65	0,40–0,80	0,50–0,90	0,60–1,05	0,60–1,20
	2	30	–	50	mm/r	0,35–0,65	0,40–0,80	0,50–0,90	0,60–1,05	0,60–1,20
	3	30	–	50	mm/r	0,35–0,65	0,40–0,80	0,50–0,90	0,60–1,05	0,60–1,20
N	1	130	–	150	mm/r	0,35–0,65	0,40–0,80	0,50–0,90	0,60–1,05	0,60–1,20
	2	140	–	160	mm/r	0,35–0,65	0,40–0,80	0,50–0,90	0,60–1,05	0,60–1,20
	3	140	–	160	mm/r	0,35–0,65	0,40–0,80	0,50–0,90	0,60–1,05	0,60–1,20
	4	130	–	150	mm/r	0,35–0,65	0,40–0,80	0,50–0,90	0,60–1,05	0,60–1,20
	5	120	–	140	mm/r	0,35–0,65	0,40–0,80	0,50–0,90	0,60–1,05	0,60–1,20
	6	150	–	170	mm/r	0,35–0,65	0,40–0,80	0,50–0,90	0,60–1,05	0,60–1,20
S	1	10	–	20	mm/r	0,15–0,30	0,20–0,30	0,20–0,40	0,25–0,45	0,30–0,50
	2	10	–	20	mm/r	0,15–0,30	0,20–0,30	0,20–0,40	0,25–0,45	0,30–0,50
	3	30	–	40	mm/r	0,20–0,30	0,20–0,40	0,30–0,50	0,30–0,60	0,35–0,65
	4	30	–	40	mm/r	0,20–0,30	0,20–0,40	0,30–0,50	0,30–0,60	0,35–0,65