

UNI - I	UNE - E	AISI - US	condition	material group
28 Mn 6	28 Mn 6, 36 Mn	1330	var ¹	2-3
2 C 30, 080 M 30	2 C 30	—	var ¹	2-3
2 C 35, C 35	2 C 35, C 35 k	—	var ¹	2-3
C 36	C 38 k	1035	var ¹	2-3
2 C 40, C 40	2 C 40, C 42 k	1040	var ¹	2-3
2 C 45, C 45	2 C 45, C 45 k	—	var ¹	2-3
C 43	C 42 k	1045	var ¹	2-3
2 C 55, C 55	2 C 55, C 55 k	—	var ¹	4-5
2 C 50, C 50	2 C 50, C 55 k	1050	var ¹	2-3
C 48	C 48 k	1050	var ¹	2-3
2 C 60, C 60	2 C 60	—	var ¹	4-5
50 CrV 4	F.1430	6150	var ¹	6-9
—	—	613	var ¹	10-11
100 Cr 6	—	52100	var ¹	6-9
100 CrMo 7	—	A 485/2	var ¹	6-9
—	—	E-3310	var ¹	6-9
—	—	5120	var ¹	6-9
100 CrMo 7	—	A 485/3	var ¹	6-9
X 45 Cr 13	—	—	var ¹	10-11
X 105 CrMo 17	—	440 C	var ¹	10-11
X 80 MoCrV 44	—	—	var ¹	10-11
X 82 WMoV 6 5	—	M2 regular C	var ¹	10-11
X 75 WCrV 18	—	T 1	var ¹	10-11
X5 Cr 13	—	410 S	FE	12
X 6 CrA 13	—	405	FE	12
X 12 CrS 13	—	416	FE	12
X 12 Cr 13	—	410	MA	12
—	—	420	MA	12
X 8 Cr 17	—	430	FE	12
X 20 Cr 13	—	420	MA	12
—	—	403	MA	12
—	—	420	MA	13.1
—	—	420	MA	13.1
X 15 CrNi 16	—	431	MA	13.1
X 10 CrS 17	—	430 F	MA	13.1
—	—	440 B	MA	13.1
X 8 CrMo 17	—	434	MA	13.1
—	—	440 C	MA	13.1
X 5 CrNi 18 10	—	304	AU	14.1
X 8 CrNi 18 12	—	305	AU	14.1
X 10 CrNiS 18 09	—	303	AU	14.1
X 2 CrNi 18 11	—	304 L	AU	14.1
—	—	304 L	AU	14.1
X 12 CrNi 17 07	—	301	AU	14.1
—	—	304 LN	AU	14.1
—	—	—	DU	14.2
—	—	201	DU	14.2
X 5 CrNiMo 17 12	—	316	AU	14.1
X 2 CrNiMo 17 12	—	316 L	AU	14.1
X 2 CrNiMoN	—	316 LN	AU	14.1
—	—	—	DU	14.2
—	—	—	MA	13.1
X 2 CrNiMoN 17 13	—	316 LN	AU	14.1
—	—	316 L	AU	14.1
—	—	317 LN	AU	14.1
X 2 CrNiMo 17 13	—	316 L	AU	14.1
X 5 CrNiMo 17 13	—	316	AU	14.1
X 2 CrNiMo 18 16	—	317 L	AU	14.1
—	—	—	AU	14.1
—	—	316 LVM	AU	14.1
—	—	329	DU	14.2
—	—	2205	DU	14.2
—	—	310 mod	S-AU	14.3
X 2 CrNiMo 17.12	—	17-7 PH	AU-PH	14.4
—	—	439, 430 Ti	FE	12
—	—	409	FE	12
—	—	632	AU	14.1
—	—	630	AU	14.1
X 6 CrNiTi 18 11	—	321	AU	14.1